



HIGH PERFORMANCE VpCI® PACKAGING

CorrLam™ VpCI® Barrier Laminate, Patent Pending



DESCRIPTION

This unique structure consists of an outer layer of high strength cross-laminated HDPE film, with a foil middle layer, which are both laminated to VpCI-126 polyethylene film. This multilayered high performance laminated structure was developed to meet the toughest industrial requirements, provides an excellent barrier to water vapor, gas, ultraviolet light and odor. The barrier layer (foil) prevents the VpCI molecular vapor from escaping from the package thereby trapping the protective chemistry within.

CorrLam VpCI Barrier Laminate prevents corrosion on metal parts, extends product shelf life and provides long-term preservation.

APPLICATION

- CorrLam is designed for the exceptional protection of moisture-sensitive and oxygen-sensitive metal parts
- Ideal for vacuum packaging
- Utilized for fabrication of large format equipment covers and small parts pouches
- For ocean shipment the use of VpCI-132 foam pads in combination with CorrLam VpCI Barrier Laminate is recommended

FEATURES

- Protects ferrous and nonferrous metals
- Utilizes Vapor phase Corrosion Inhibitor (VpCI) technology
- Eliminates the need for desiccants while providing complete corrosion protection
- Flexible, heat-sealable (vacuum sealable)
- High barrier block to water vapors, oxygen and carbon dioxide
- Excellent mechanical properties
- Water Vapor Transmission Rate (WVTR) and O₂ Transmission Rate (OTR) are less than 0.001g/100 in² (0.001g/6.45m²) per day
- High degree of puncture and tear resistance
- Excellent choice of material for export packaging, highly sensitive domestic packaging and/or long-term preservation.
- Material may also be fitted with a one-way vacuum valve, for removal of harmful moisture vapor and other gases from the interior of an enclosure or package
- Conforms to performance specification MIL PRF-131J



CORTEC
CORPORATION

Environmentally Safe VpCI®/MCI® Technologies

PACKAGING AND STORAGE

Available in custom sizes such as pouches, covers, blankets etc. Contact Cortec Corporation for more information. Store in a cool, dry place until ready for use. The shelf life for CorrLam VpCl Barrier Laminate material and converted products is one year.

TESTING DATA

Property	Test Method	Value
Basis Weight, Lb/ream (kg/ream)	ASTM D646	138.8 (62.95)
Yield, in ² /lb (m ² /kg)	Calculated	3100 (4.4)
Caliper, mils (mm)	ASTM D2103	8.7 (221)
Tensile strength, psi (kPa)	ASTM D882	MD 3900 (26871)
		TD 3100 (21359)
Puncture resistance, lb(g)	FED STD 101	19.5 (0.0430)
Elmendorf tear, g	ASTM D 1922	MD 750
		TD 1100
Heatseal Strength, lb/in (kg/cm), width (375°F [191°C], 40 psi, 2.0 sec. Dwell)	ASTM F88	15-20 (2.6-3.5)
Water Vapor Transmission rate, g/100 in ² , 24 hours (100°F [38°C], 90% RH)	ASTM 1249	<0.001
Oxygen Transmission rate, cc/100 in ² , 24 hours (73° F [23° C), 0% RH)	ASTM D3985	<0.001

Note: These values are typical for this structure and should not be construed as performance specifications.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
 Phone (651) 429-1100, Fax (651) 429-1122
 Toll Free (800) 4-CORTEC, E-mail info@corotecvci.com
 Internet http://www.corotecvci.com

printed on recycled paper 10% post consumer

Revised 6/26/03. Cortec Corporation 2003. All rights reserved. Supersedes: 2/28/03. VpCl® and CorrLam™ are trademarks of Cortec Corporation.

Distributed by:



OTiK Sp. z o.o.

ul. Hutnicza 4
 81-061 Gdynia
 tel.: 58 6230498
 fax: 58 6230496

otik@use.pl

www.inhibitory.use.pl



Certificate No.70781

Certificate No 81867