





## M-640

#### **PRODUCT DESCRIPTION**

M-640 is a corrosion inhibiting additive for water and ethylene glycol-based engine heat exchange fluids. It protects ferrous and non-ferrous metals from corrosive contaminants. This product is an excellent replacement for phosphate/nitrite-based/amine compounds. M-640 is based on an organic-inorganic formulation designed for low level concentrations in field applications. M-640 contains a unique combination of contact and vapor phase corrosion inhibitors that provides corrosion protection even in partially filled spaces. For situations with extremely hard water, or requiring more vapor phase protection, use M-640 SC.

#### **FEATURES**

- Protects ferrous and non-ferrous metals from corrosion and pitting
- Nitrite, chromate and heavy metal free
- Contains contact and vapor phase corrosion inhibitors
- Economical
- Use in low dosages
- Environmentally acceptable

### **PHYSICAL PROPERTIES**

Appearance Lavender powder pH 11.5-12.0 (1% solution)

Non-volatile Content 99.5-100% Solubility in Water 40% by weight

#### **TEST DATA**

ASTM D-1384-87 (Standard Test Method for Engine Coolant in Glassware) for engine antifreeze/coolants treated with M-640:

Weight Loss per Specimen (mg)			
Additive	Copper	Brass	Solder
0.5% M-640	6-9	1-2	8-9
ASTM D-3306 Requirements	≤10	≤10	≤30
GM 1899 M Requirements	≤10	≤10	≤20
GM 1825 M Requirements	≤10	≤10	≤20
Additive	Carbon Steel	Cast Iron	Aluminum
0.5% M-640	1-2	4-6	1-2
ASTM D-3306 Requirements	10	10	30

10

10

10

20

20

### **TYPICAL APPLICATIONS**

GM 1899 M Requirements

GM 1825 M Requirements

M-640 is an additive to antifreeze/coolant fluids to replace nitrites, phosphates, amines and other types of restricted corrosion inhibitors. Use M-640 SC if extremely hard water or high vapor phase protection is required.

The final concentration range for M-640 under operating conditions is 0.5-0.8% by weight.



#### **PACKAGING AND STORAGE**

M-640 is available in 100 pound (45 kg) polyethylene lined drums. Store in a sealed container in a dry warehouse, avoiding direct exposure to sunlight, with temperatures not exceeding 150°F (66°C). Under these conditions, shelf life is up to 24 months.

# FOR INDUSTRIAL USE ONLY KEEP OUT OF REACH OF CHILDREN KEEP CONTAINER TIGHTLY CLOSED NOT FOR INTERNAL CONSUMPTION CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

#### **LIMITED WARRANTY**

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA Phone (651) 429-1100, Fax (651) 429-1122 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com Internet http://www.cortecvci.com

printed on recycled paper 10% post consumer
Revised 10/30/98. Cortec Corporation 1998. All rights reserved. Supersedes: 2/98.



OTiK Sp. z o.o. ul. Hutnicza 4 81-061 Gdynia tel.: 58 6230498 fax: 58 6230496 otik@use.pl www.inhibitory.use.pl



Complete and the A 1784 S.