



SURFACE PREPARATION PRODUCTS

VCI-423 Gel

PRODUCT DESCRIPTION

VCI-423 is a rust remover that is harmless to people while effectively removing rust and tarnish from steel, iron, copper, brass, chrome and aluminum. VCI-423 removes corrosion from metal without creating waste disposal difficulties.

When used as recommended, VCI-423 will not harm human skin or adversely affect most paints, plastics, wood, textiles, ceramics or rubber. Removing corrosion from metal is easy. Apply VCI-423 and rinse with water and use Cortec® VCI-414 or VCI-419 for added protection.

VCI-423 is completely organic and 100% biodegradable, and does not have special disposal requirements for typical use. Waste treatment may be required if a sufficient quantity of pollutants (oil, solvents, dirt, grease) are introduced into the chemical solution.

Unlike conventional rust removers which can be extremely dangerous to use, handle and store, VCI-423 is so mild that minimal protective covering is needed. In addition, the non-toxic, non-flammable formulation has no pungent acid fumes. Being nearly odorless and extremely mild makes VCI-423 easy to use.

VCI-423 is formulated to stay in place for special applications that require the chemical to cling to vertical surfaces or the underside of horizontal surfaces. VCI-423 makes it easy to remove rust from tanks, vessels, outdoor machinery and equipment, walls, fences, railings and vehicles.

FEATURES

- USDA approved
- Removes rust and corrosion from ferrous and non-ferrous metals
- Prevents flash rusting
- Completely organic and biodegradable
- Non-polluting and environmentally acceptable for easy disposal
- Loosens rust-frozen parts
- Cleans rust stains from painted, wooden and other surfaces
- Safe to handle, use and store
- No adverse effects on most paints, plastics, wood, textiles, ceramics and rubbers
- Safe, non-toxic, non-flammable formulation and mild odor makes it ideal for in-plant use
- Gel form allows application on vertical or upside-down horizontal structures

TYPICAL APPLICATIONS

- In-process rust removal for parts and metal stock
- Interior and exterior surfaces of tanks and vessels
- Outdoor machinery and equipment
- Trucks, cars and other vehicles
- Automotive, marine and farm parts and equipment
- Fences, railings and walls
- Tools, locks and rust-frozen parts

APPLICATION

VCI-423 can be applied using spray equipment, including air and airless spray, as well as by brush dip.

For spray, brush or roll-on applications, remove loose rust. Then apply VCI-423 concentrate to the surface, let product stand for 10-15 minutes and rinse with Cortec® VCI-410 series (typically, little or no rubbing is required). Reapply if necessary. Medium and heavy rust will take somewhat longer.

For dip application, remove heavy deposits or loose rust or tarnish. Soak part(s) in tank as long as required to remove corrosion. Remove from tank and rinse with Cortec® VCI-410 series (VCI-414/416) for added protection.

Increasing temperature up to 110°F (43°C) will speed the cleaning process.

PHYSICAL PROPERTIES

Appearance	Dark brown gel
Non-volatile Content	42-47%
Density	9.7-10.0 lb/gal (1.16-1.20 kg/l)

RECOMMENDED SPRAY APPLICATION

For good atomization and spray pattern, use the following:

- Graco Air Assisted Airless High Pressure Gun, Model AA Plus
- Pump - 41:1 SST Bulldog, SP 5 gallon (19 liter) Ram with ram SSP plate extension
- Adapter - SST ram plate or 55 gallon (208 liter) DP ram and SST ram plate
- Tip - 715 (SST)
- Hose - 3/8" x 25' Teflon (5 cm x 7.6 m)
- Cap - Standard with high flow needle and seat operating pressure of 3300 psi (228 bar)
- Filter - HP SST 100 mesh

PACKAGING AND STORAGE

VCI-423 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes and bulk. Store in a heated warehouse to avoid freezing.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@corotecvci.com
Internet www.corotecvci.com

Distributed by:



OTiK Sp. z o.o.

ul. Hutnicza 4
81-061 Gdynia
tel.: 58 6230498
fax: 58 6230496

otik@use.pl

www.inhibitory.use.pl

printed on recycled paper 10% post consumer

Revised 9/25/00 . ©Cortec Corporation 2000. All rights reserved. Supersedes: 9/9/98.



Certificate No. 43345